

1

traditional

C

performance/testing

BEST

DESCRIPTION/TEST METHOD	STANDARD REQUIREMENT	BEST: TEST RESULTS
Dimensional Deviations AS/NZS 4456.3	+/- 2mm	+/- 2mm
Characteristic Breaking Load (kN) AS/NZS 4456.5	> 2.0 (40mm) > 5.0 (60mm) > 10.0 (80mm)	4.46 (40mm) 9.90 (60mm) 13.10 (80mm)
Abrasion Resistance (mean abrasion index) AS/NZS 4456.9	No Limit (low volume) < 5.0 (medium volume) < 3.5 (high volume)	Not Applicable (40mm) 4.5 (60mm) 3.2 (80mm)
Slip Resistance (co-efficient of friction) AS/NZS 3661.1	> 0.4	0.7
Salt Resistance (cycles) AS/NZS 4456.10	> 40 Cycles	No deterioration after 40 cycles

N.B.: Performance results are typical BEST values. BEST will on request, generate specific product test results.

